



# PS 100

General Purpose Polystyrene for Injection Molding

## Product Description

General purpose Polystyrene PS 100 is manufactured by continuous mass polymerization of styrene monomer. It is a crystal-like, hard and brittle polymer with good flow properties and high clarity. It is designed for medium and thin wall thickness articles and gives broad processing window for molding applications.

## Typical Applications

It is recommended for the manufacture of packaging items such as plastic boxes and typical applications include cutlery, tumblers, office stationery items, jewelry boxes, medical supplies or any clear injection molded items.

## Typical data

Properties	Unit	Value <sup>(1)</sup>	ASTM Method
<b>Resin Properties</b>			
Melt Flow Rate @ 200°C & 5 kg load	g/10 min.	14	D-1238
Density @ 23°C	kg/m <sup>3</sup>	1050	D-792
Bulk Density (Method B)	kg/m <sup>3</sup>	600	D-1895
<b>Mechanical Properties <sup>(2)</sup></b>			
Tensile Strength	MPa	40	D-638
Tensile Elongation	%	2	D-638
Tensile Modulus	MPa	2254	D-638
Flexural Strength	MPa	72	D-790
Flexural Modulus	MPa	3529	D-790
Izod Impact Notched @ 23°C	J/m	12	D-256
Rockwell Hardness, L-Scale	-	94	D-785
M-Scale	-	64	D-785
<b>Thermal Properties <sup>(2)</sup></b>			
Vicat Softening Point (Rate A, 1 Kg/50°C)	°C	92	D-1525
Heat Deflection Temperature (Method B, 455 KPa, Annealed)	°C	87	D-648
Flammability Rating, UL 94 @ 1.3 mm and 3 mm (natural color)	Class	HB	-

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

## Processing Conditions

Typical temperature (°C) profile for injection grade PS 100:

Throat	Feed	Transition	Metering	Die
Ambient	160	190	210	205

## **Food Regulation**

PS 100 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

## **Storage and Handling**

Polystyrene resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PS resin within 6 months after delivery.

---

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia  
Tel: 966 1 2258000  
Fax: 966 1 2259000

Technical Marketing  
Tel: 966 1 2659166  
Fax: 966 1 2653544  
Toll-free 800 1245577

PS Sales:  
Fax: 966 1 2258751  
Website: [www.sabic.com](http://www.sabic.com)

---

*NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.*